

PRODUCT BULLETIN
GYPSUM PRODUCTSGYPSUM BOARD
5/8" NULL-A-FIRE (UL)
TYPE XBULLETIN NO: B-6
DATE: 3/1/74
PAGE: 2 of 3

APPROVALS:

GJL
BBK P.M.F. 2/14

ASTM C 36

CANCELS: B-6
DATE: 2/15/73PRODUCT SPECIFICATIONS (Refer to Product Bulletin B-G-4 for General Specifications)

	Long Beach Antioch & Seattle	Jacksonville & Delanco
Wet Weight (lbs/MSF)	3050 - 3300	3200 - 3500
Dry Weight (lbs/MSF) (UL minimum - 2080)	2100-2250 Average 2150	2150 - 2350 Average - 2225
Evaporation Loss (lbs/MSF)	900 - 1050	1050 - 1200
Thickness - Average (inch) (UL minimum - 0.595)	0.600 - 0.625 Average - 0.610	0.600 - 0.625 Average - 0.610
Thickness - Individual Reading - (inch)	± 0.010 from average	± 0.010 from average
Profile - Movable Partition Board - KW-500, KW-700	Variations in surface of back plane shall not be greater than 0.005" within a 6" span measured across the width.	
Edges - Movable Partition Board	Bevel edge; Tapered edge on special order	
Edge Hardness at take-off (lbs)	10 minimum - 14 average - 18 maximum	
End Peel after sawing (inch)	1/8 maximum	
	<u>All Plants</u>	
Flexural Strength (minimum)		
Across grain (lbs)	180	
Parallel (lbs) (UL minimum - 62)	62	
Deflection at Break (minimum)		
Across grain (inch)	0.25	
Parallel (inch)	0.15	
Punch Test (lbs)	600 - 1000	
Modulus of Rupture	260 maximum	